



Europäisches Patentamt

European Patent Office

Office européen des brevets



(11) Publication number : **0 470 760 A2**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number : **91307049.6**

(51) Int. Cl.⁵ : **B32B 27/08**

(22) Date of filing : **31.07.91**

(30) Priority : **09.08.90 GB 9017500**
17.08.90 GB 9018056

(43) Date of publication of application :
12.02.92 Bulletin 92/07

(84) Designated Contracting States :
DE FR GB IT

(71) Applicant : **BXL Plastics Limited**
Belgrave House, 76 Buckingham Palace Road
London SW1W 0SU (GB)

(72) Inventor : **Leese, Leonard**
6 Valley Close, Brantham
Manningtree, Essex CO11 1GG (GB)
Inventor : **Yadav, Vijay**
14309 Blue Granite Road
Pineville, North Carolina 28134 (US)

(74) Representative : **Krishnan, Suryanarayana**
Kalyana et al
BP INTERNATIONAL LIMITED Patents &
Agreements Division Chertsey Road
Sunbury-on-Thames Middlesex TW16 7LN
(GB)

(54) **Composite plastics film or sheet.**

(57) This invention relates to a composite film comprising three coextruded layers including a core layer sandwiched between two outer layers, the core layer having been stretch-voided. At least one of the outer layers has an external printable surface and comprises at least three thermoplastic polymeric materials of which one is a rubbery polymer and at least a further two of the materials have a degree of mutual incompatibility, said external printable surface being substantially free of particle-induced voids. The films are suitable for use as synthetic paper.

EP 0 470 760 A2

BEST AVAILABLE COPY

This invention relates to a composite plastics film or sheet having an external printable surface for use as a synthetic paper or for coating to produce a synthetic paper and to a method for its production.

The term "synthetic paper" is used herein to mean plastics film and sheet products having a feel and printability similar to cellulose paper.

5 Synthetic papers have been produced commercially by the Plastics Industry for many years and have taken a number of different forms. These have included products having voided (ie multicellular) or unvoided structures, some of which have been coated with filler-and/or pigment- containing surface coatings to improve printing qualities.

10 Descriptions of plastics compositions and methods for producing synthetic papers can be found in our GB-A-1470372, GB-A-1492771 and GB-A-1490512. Further, a description of particularly advantageous coatings can be found in our GB-A-2177413. The concepts of all the aforementioned specifications are included herein by reference.

15 Each of the above-mentioned voided and unvoided structure types has its own advantages. In particular, the voided structure generally has an inherent resilience rendering it particularly suitable for certain types of printing whereas unvoided material lends itself more readily to heat-sealing due to absence of cell collapse and attendant distortion which can otherwise occur.

A disadvantage of voided structures of the type produced by stretching a two-phase system, whereby the voids are induced, and where some of the voids extend through the surface, is that the void-inducing particles of the second phase, whether they be organic or inorganic, give rise to a surface dust which can contaminate production equipment and printing machinery. This is highly undesirable. Further, the nature of plastics compositions useful in the production of such structures can also give rise to undesirable deposits on processing equipment. In particular, extrusion die lips can become encrusted with a deposit and calendering or conditioning rollers can become coated with a type of deposit commonly referred to as plate-out and such deposits interfere with satisfactory continuous operation.

25 Contamination of printing machinery may be overcome by washing or coating the stretched product prior to printing but even in cases where these measures are satisfactory, they add to the overall cost of the end product and do not overcome the up-stream problems.

30 It has been proposed in GB-A-2099754 to coextrude a stretch-voidable substrate with surface layers having a lower filler content, stretching the composite monoaxially then melt-laminating a plastics layer to one surface and stretching the composite in a direction at right angles to the first direction in order to achieve a paper-like product without the above-mentioned dust and die contamination problems.

35 It has also been proposed in US-A-4582753 and US-A-4702954 to produce a polymer laminate by coextruding a stretch-voidable substrate with a water vapour barrier layer and optionally a transparent and/or pigmented skin layer and then stretching the product biaxially. While the stretch-voidable substrate may be located between barrier and/or skin layers a barrier layer is always attached to a substrate layer either directly or via a conventional adhesive resin and comprises a polymeric composition having water vapour absorbent capability with or without the aid of a hygroscopic additive.

40 ~~US-A-4377616~~ proposes the production of an opaque biaxially oriented polymer film structure of lustrous satin appearance comprising a stretch-voided core layer and void-free transparent skin layers. The stretched composite which may be produced from an initial coextrudate is said to be suited for food packaging (due to low water vapour and oxygen transmission characteristics) and as decorative wrapping material.

45 The prior art discussed above seeks to overcome the problems which may be associated with the manufacture of synthetic paper comprising a stretch voided structure in a complex way albeit involving coextrusion but also sequential biaxial stretching and lamination. Whereas the production of packaging materials comprising internal stretch voided structures are otherwise proposed, these incorporate specific water vapour barrier layers or external transparent layers consistent with their intended application.

50 Additional prior art includes GB-A-2224973, GB-A-2177049, EP-A-258020, US-A-4701370, US-A-4663216, US-A-4632869 and US-A-4438175. In so far as the disclosures of these references relate to stretched coextruded composite structures comprising a voided substrate to which is attached a non-voided skin or outer layer, they are directed towards products wherein the skin layer is either free of pigment or filler, or the content of such is low. Otherwise, in this context, the disclosures are general and do not give any indication of the amounts of pigments or fillers used for skin layers in any of the examples where such are incorporated. Accordingly, the die crust problems associated with high filler contents are avoided in these references which infer minimising the incorporation of fillers and/or pigments in the outer layers of such coextrudates.

55 We have found that a composite plastics film or sheet for use as a synthetic paper can be produced by initial coextrusion of a core layer and outer layers, without a significant die crust problem associated with an outer layer to provide an external printable surface if that outer-layer comprises three or more thermoplastics polymeric materials of which one is a rubbery polymer and at least a further two of which have at least a degree

of mutual incompatibility.

The above-mentioned combination of three or more thermoplastics materials permits high proportions of filler and/or pigment to be incorporated while minimising die deposits and the rubbery polymer additionally increases the cohesive strength of the external surface and its adhesive bond directly or indirectly to the core layer, whether or not filler and/or pigment is incorporated.

Accordingly, the present invention is a composite film or sheet for use as synthetic paper comprising three coextruded layers including a core layer situated between two outer layers, the core layer having been stretch-voided, characterised in that at least one of the outer layers provides an external printable surface, optionally after further treatment, and comprises at least three thermoplastics polymeric materials of which one is a rubbery polymer and at least a further two of the materials have at least a degree of mutual incompatibility, said external surface being substantially free of particle-induced open voids.

Also provided by the present invention is a method for producing such a composite plastics film or sheet.

The layers may be coextruded using coextrusion equipment known in the plastics industry which may comprise one extruder for each plastics composition employed and is adapted to feed a coextrusion die fitted for example with appropriate flow distribution control or to feed a conventional die via an appropriate distributor block.

The core layer may comprise any stretch-voidable composition but is preferably a composition such as is described in our published GB-A-1470372 and GB-A-1492771. More preferably, the composition of the core material comprises a blend of an orientable thermoplastics olefin polymer with at least one metal resinate which is 2 to 502 by weight calculated on this blend and is at least partially incompatible with the olefin polymer. The metal resinate preferably forms, at least in part, a separate phase uniformly distributed within the olefin polymer and the total composition is capable of being extruded to form a layer and stretched to produce a voided structure. Most preferably, the composition of the core comprises a blend, within the aforementioned range, of a high density polyethylene and a calcium-zinc resinate. In a preferred embodiment of this invention the composition of the core layer is selected from:-

	<u>Parts by weight</u>
High density polyethylene (copolymer)	100
Calcium-zinc resinate	5-15
Polystyrene	4.5-5.5
High density polyethylene (homopolymer)	17.5-21
Calcium carbonate filler	15-25
Titanium dioxide	5-10
Styrene-butadiene copolymer	0-1.0
Calcium Oxide	0.4-1.0

The above compositions may contain other additives such as an antioxidant and a lubricant. While an anti-static agent may be incorporated, we have found it preferable to incorporate such an agent in the compositions of one or more of the outer layers and/or in coatings when antistatic properties are required.

The term high density polyethylene is meant to include, unless otherwise indicated, polymers and copolymers of ethylene with minor amounts of other alpha-olefin monomers as is commonly understood in the industry and as described in the above-mentioned British patent specifications. The term includes mixtures of high density polyethylenes.

As indicated above the composition of the core layer may include additives additional to the stretch-voidable components examples of such additives are more generally discussed in our British Patent Specifications 1470372 and 1492771. It is preferred that voids in the core layer are produced solely by stretch-voiding.

The outer layers of the coextrudate and which each comprise thermoplastics material may be comprised of the same composition. This permits the use of a single extruder for the composition and simple coextrusion die with an internal or ancillary distributor for example. At least one of the outer layers should comprise an extrudable thermoplastics composition, which can be extrusion-bonded, with or without intermediate bonding or other layers, to the core layer and stretched at about the temperature at which the core layer is stretch-voided, and should comprise at least two thermoplastics polymeric materials having at least a degree of mutual incompatibility and a thermoplastics rubbery polymer. The composition and stretching should be such that substantially no particle-induced stretch-voiding occurs to form any open voids on the intended external printable

surface of this layer. The outer layer so produced is preferably translucent or opaque and can be further treated, if necessary, to improve printability of this surface. It is preferred, however, that the base thermoplastics material of at least one outer layer, preferably both outer layers, which is destined to provide an external printable surface is not water-vapour absorbent and that the composition does not contain a particulate or microfibrinous hygroscopic solid, especially polymeric, additive which renders the layer water-vapour absorbent. It is preferred also that any layer intermediate this layer and the core layer fulfils this preferred requirement. In this way a degree of product stability can be achieved.

By "an external printable surface" we mean a surface textured or modified as by virtue, for example, of the presence of pigment and/or filler and/or incompatible polymer or resin and/or by the influence of a sub-surface and having a printability corresponding to a wettability of at least 40 dynes/cm.

It will be appreciated that when the composition of the outer layer destined to provide an external printable surface is non-polar or insufficiently polar to inherently provide the required printability, the surface of the outer layer may be subjected to a corona discharge treatment, flame treatment or chemical treatment such as chemical oxidation treatment, for example, to render it wettable to the required degree. Such treatments are well known and it is deemed unnecessary to describe them here.

The thermoplastics materials on which the compositions of the outer layers are principally based are preferably at least similar to the thermoplastics material which predominates in the core layer composition whereby suitable extrusion temperatures and stretching temperatures do not seriously conflict. In such a case direct melt bonding between adjacent layers as they come together can be achieved thereby obviating the need for any intermediate bonding layers or the so called tie layers. Further, if at least the major polymer components in the core and outer layers are similar, it can improve the process economics by allowing reworking of reclaimed scrap material, eg the sheet edge trims into, eg the core layer composition.

In particular, when the core layer is based on high density polyethylene for example, at least one of the outer layers, and particularly that destined to provide an external printable surface, is preferably principally based on high density polyethylene also. The effect of stretch-orientation on the physical properties of a thermoplastics layer can be to increase stiffness and tensile modulus which is especially valuable to improve handling where the product is to be sheeted and then printed. Such properties can be improved if a mixture of two or more thermoplastics resins is employed whereby the surface characteristics of a layer may be modified when the layer is stretched, especially if the resin components have a degree of mutual incompatibility.

In accordance with this invention, at least one of the outer layers destined to provide an external printable surface should comprise a mixture of two or more thermoplastics resins, including at least two having at least a degree of mutual incompatibility, and a thermoplastics rubbery polymer. It is believed that the rubbery polymer serves to control the bond strength between the resins, to assist in substantially preventing particle-induced stretch-voiding and formation of open voids at least on the intended external printable surface of the layer, to improve surface strength and to improve interlayer bonding, particularly of the outer layer to the core layer. Importantly, the mixture of resins and rubber polymer of this outer layer aids processing and minimises die deposits, particularly for filled and/or pigmented materials. It should be appreciated that the resins and the thermoplastics rubbery polymer, in this immediate context, should be such that there is a temperature at which they are all molten, or at least soft, and can be blended together.

Thus, the latter layers may comprise a mixture of 100 parts of base resin comprising high density polyethylene or a propylene (co)polymer, from 5 to 100 parts by weight of a styrene polymer and from 0.5 to 20 parts of a rubbery polymer (preferably 1 to 10 parts) consistent with the preferred embodiment described in our GB-A-1490512 including the modifications described therein.

We have found that blends of two or more of high density polyethylene, linear low density polyethylene, a propylene (co)polymer and polystyrene, two of which have at least a degree of mutual incompatibility, together with a rubbery polymer are particularly advantageous.

As examples of thermoplastics rubbery polymers there can be mentioned a copolymer of butadiene and styrene having a butadiene content of from 70% to 90% by weight; Duradene (Registered Trade Mark) supplied by ISR Ltd which is a 75:25 butadiene:styrene copolymer; Solprene (Registered Trade Mark) 1205 supplied by Phillips Petroleum Ltd which is a 75:25 butadiene:styrene block copolymer; Cariflex TR1102 which is a styrene:butadiene:styrene block copolymer. Also there can be mentioned a copolymer of isobutylene and isoprene. Butyl 402 rubber supplied by Polymer Corporation Ltd is a 97.3:2.7 isobutylene:isoprene copolymer. EPDM rubbers comprising ethylene propylene diene terpolymers can also be mentioned and clearly any equivalents of the aforementioned proprietary rubbers are deemed to be mentioned by inference.

The amount of thermoplastics rubbery polymer to be employed in the composition of an outer layer destined to provide an external printable surface is advantageously in the range 0.5 to 20, preferably 1 to 10 parts by weight based on 100 parts by weight of the principal thermoplastics polymer component.

In a preferred embodiment of this invention and subject to the minimum requirements thereof, the compo-

sition for the layer destined to provide an external printable surface and which is an opaque layer is selected from:-

	<u>Parts by weight</u>
5 High density polyethylene copolymer	100
Linear low density polyethylene	0-43
Low density polyethylene	3-11
10 Polystyrene	0-25
Styrene butadiene copolymer	0-4
Polypropylene/propylene copolymer	0-16
Pigment/filler	22-50
15 High density polyethylene homopolymer	3-24

However, to obtain a translucent outer layer destined to provide an external printable surface, the composition may be selected from:-

	<u>Parts by weight</u>
20 High density polyethylene copolymer	100
Filler/pigment	0-38
25 Low density polyethylene	0-3.2
Polystyrene	0-40
Styrene butadiene copolymer	0-8
30 Polypropylene/propylene copolymer	0-14
Ethylene vinyl acetate copolymer	0-6
High density polyethylene homopolymer	0-20

35 The above compositions may also include other additives such as a lubricant (0-0.4 parts by wt), eg a wax, stearic acid or a metal stearate, especially calcium stearate; and an antistatic agent (0-2, preferably 0.5-1.5 parts by wt based on 100 parts of the principal polymer component of the composition comprising each outer layer) of the ethoxylated amine type.

40 It has been found that the presence of fillers and/or pigments in the outer layer(s) can provide a better grip during stretching of the co-extruded layers.

In particular when the stretching process employs a flat-bed stretcher with edge grippers, the pigment/filler content is preferably in the range 10 - 30%, especially 15 - 25% by weight of the composition.

45 The thickness of the outer layers in relation to the core layer is preferably such that at least one layer destined to provide an external printable surface derives such surface at least in part from the stretch-voided core layer. Accordingly, the thickness of such outer layer is suitably no more than 25%, preferably no more than 10% of the thickness of the core layer. The thickness of the other outer layer is preferably the same to achieve a balanced product.

50 The stretching of the coextruded layers may be uniaxial or biaxial according to known methods. Simultaneous biaxial stretching is preferred and this may be effected eg by co-extruding the layers in the form of a tube and inflating it in known manner. However, to achieve a flat laying product, the layers are preferably coextruded to form a continuous sheet or web which is then stretched employing a flat-bed stretching apparatus preferably of the type described in our published GB-A-1374574 and GB-A-1442113. Stretching of thermoplastic webs using such apparatus is described in our published GB-A-1490512. The methods described in these patents are incorporated herein by reference. Webs stretched from compositions comprising 100 parts by wt of a high density polyethylene and/or polypropylene and 0-100 parts by wt of polystyrene are most preferred.

55 It is preferred that the stretching of the coextruded layers is carried out at a temperature within the normal orientation temperature range of the principal thermoplastics polymer on which the core layer is based. The temperature of stretching is also preferably within the normal orientation temperature range of the principal ther-

moplastics polymer on which the outer layer destined to provide an external printable surface is based.

As defined in the aforementioned GB-A-1470372 and GB-A-1492771, by "normal orientation temperature range" there is meant that range of temperatures well known to those skilled in the art, bounded at the lower end by the minimum temperature at which uniaxial stretching of the thermoplastics material can be effected at a commercially acceptable rate and at the upper end by the maximum temperature at which stretching of the thermoplastics material can be effected to achieve a significantly oriented product.

The temperature of stretching the coextruded layers is further preferably selected from:

a) temperatures below the melting point or softening point of the void inducing component of the core layer when said component is a non-polymeric organic compound, a metal salt of an organic acid, a metal resinate or a modified or unmodified rosin ester;

b) temperatures below the glass transition temperature of the void inducing component of the core layer when said component is a polymer such that voids are formed in the core layer.

The composite plastics film or sheet produced according to this invention may be subjected to various treatments and surface coating for example to enhance antistatic and printing qualities. It will be understood however, that the outer layer destined to provide an external printable surface when based on polyolefins for example, will usually be subjected to surface treatment such as oxidation via flame or corona discharge treatment to provide a more polar surface and the required wettability to more readily accept inks and coatings. Clearly, such treatments may be applied to the surface of the other outer surface if desired.

Coatings that may be applied to the composite film or sheet include aqueous coatings commonly used in the paper industry and especially latex-based coatings. Of particular value in the present context however, are the coatings described in our GB-A-2177413 as herein before mentioned. It will be appreciated that adhesive coatings such as pressure sensitive and heat activatable coatings may be alternatively or additionally applied to the composite film and sheet products of this invention as may be desirable for particular applications.

The application of surface coatings to the composite plastics film and sheet products of this invention can improve their stiffness as well as improve antistatic and printing qualities. However, the basic sandwich type structure can provide better inherent stiffness than that of a sheet made only of similar core or outer layer material. Dust-free films and sheets of this invention have a compressible core layer which is of value in letterpress printing and protect processing machinery from unwanted deposits.

The following Examples are given to illustrate the invention but in no way limit the scope thereof.

Example 1

The following composition was used to produce Compound 'A' (used in the production of the core material).

Parts by weight

5	Rigidex 002/55 high density polyethylene (copolymer) of MFI* 0.2 g/10 min and density 0.955 Kg/m ³ (supplied by BP Chemicals Ltd (BPCL))	100
10	Rigidex HD6070EA high density polyethylene of MFI 7.5 and density 0.96 Kg/m ³ (supplied by BPCL)	17.6
15	Polystyrene Grade HF888 (supplied by BPCL)	4.8
	Ennesin ZCl4 (Calcium-zinc resinate) (supplied by Leon Frenkel Ltd)	9.6
20	Cariflex TR1102 Styrene-butadiene-styrene block copolymer (supplied by Shell UK Ltd)	0.6
25	Calcium Carbonate-anhydrous 2.5 micron particle size (supplied by Himont UK Ltd)	21.0
	Titanium dioxide (Rutile) (RCR2 supplied by Himont UK Ltd)	5.8
30	Armostat 400 (antistatic agent) (supplied by AKZO Chemicals Ltd)	0.14
	Armostat 375D (antistatic agent) (supplied by AKZO Chemicals Ltd)	0.35
35	Caloxal CPA calcium oxide (supplied by Sturge Lifford Ltd)	0.58

Parts by weight

40	Calcium Stearate (supplied by RTZ Chemicals Ltd)	0.04
45	Irganox B215 antioxidant (supplied by Ciba Geigy Industries Ltd)	0.29
	*MFI = Melt Flow Index	

50 Compound A was prepared from this composition as follows:-
Separate, melt blended, cooled and diced masterbatches were obtained from the above with the calcium carbonate and titanium dioxide respectively and comprised:-

A1

Calcium Carbonate 60%
 Rigidex HD 6070EA 39.6%
 Armostat 400 0.4%

A2

Titanium dioxide 60%
 Rigidex HD 6070EA 39.6%
 Calcium Stearate 0.4%

Masterbatches A1 and A2 were then intermixed in appropriate proportions with the remainder of the ingredients of the composition and fed to a compounding extruder. The composition was melt blended at approximately 200° C extruded, cooled and diced to form Compound A.

The following composition was used to produce compound 'B' (used in the production of the outer layer material):-

Parts by weight

Rigidex 002/55
 high density polyethylene (copolymer) 100
 Calcium Carbonate (as for Compound A) 29
 Titanium dioxide - RCR2 (as for Compound A) 12.5
 Rigidex HD 6070EA high density polyethylene 14.85
 Rigidex DFDG 0159 low density polyethylene
 (supplied by BPCL) 6.24
 Polystyrene grade HF888 (as for Compound A) 25.0
 Innovex - Linear low density
 Polyethylene grade LL0640AA
 (supplied by BPCL) 12.5
 Cariflex TR1102 4.0
 Calcium stearate (as for compound A) 0.06

Parts by weight

Nourymix AS024 4.5
 (Antistatic masterbatch - active ingredient
 40%)
 (supplied by AKZO Chemicals Ltd)
 Armostat 400 (as for compound A) 0.15

Compound 'B' was prepared from this composition as follows:- Separate, melt blended, cooled and diced masterbatches were obtained from the above with the calcium carbonate and titanium dioxide respectively and comprised:-

B1

Calcium Carbonate 60%
 Rigidex HD6070EA 39.6%
 Armostat 400 0.4%

B2

Titanium Dioxide 49.87%
 Calcium Carbonate 24.94%
 Rigidex DFDG0159 24.94%
 Calcium Stearate 0.25%

Masterbatches B1 and B2 were then intermixed in appropriate proportions with the remainder of the ingredients of the composition and fed to a compounding extruder. The composition was melt blended at approximately 200° C, extruded, cooled and diced to form Compound B.

Compound 'A' was fed to an in-line extruder of a twin extruder-distributor-sheeting die coextrusion arrangement and Compound 'B' fed to a secondary extruder. The sheeting die and distributor were of conventional construction enabling a three-layer coextrudate to be produced continuously comprising a layer of Compound 'B' on each side of a layer of Compound 'A'.

The extruders were arranged to enable each to form and feed a substantially homogeneous melt into the distributor which was maintained at a temperature of 210° C. The die lips were adjusted to approximately 5mm and the flow of each of the melts was adjusted to give a composite layered extrudate about 395mm wide at an extrusion rate of 360Kg/hr.

The composite extrudate was then fed directly onto and around a set of cooling and conditioning rollers running at a peripheral speed whereby the core material was brought to a temperature of approximately 122°C and the outer layers each to a temperature of approximately 118°C and a conditioned composite extrudate produced having an overall thickness of 1.5mm, a core thickness of 1.32mm and substantially equally thick outer layers each being 0.09mm.

The thus conditioned composite extrudate was then fed into a simultaneous biaxial stretching apparatus of the type described in our GB-A-1442113 with reference to Figures 1 to 9 of that reference and arranged to provide a 4:1 stretch in each of the longitudinal or machine direction (MD) and transverse direction (TD).

The stretching apparatus was provided with a four zone circulating air oven the zones comprising Preheat zone 1, Preheat zone 2, Stretching zone 3 and Annealing zone 4. The temperatures of the zones, lengths of the zones and sheet speeds were as follows:-

			<u>Temp</u>	<u>Length</u>	<u>Speed in</u>	<u>Speed out</u>
				<u>Metres</u>	<u>Metres/Min</u>	<u>Metres/Min</u>
	Preheat	zone 1	139 °C	1.0	10.4	-
	Preheat	zone 2	138 °C	1.0	-	-
	Stretching	zone 3	130 °C	1.5	-	43.8
	Annealing	zone 4	115 °C	2.0	43.8	43.8

The web gripping devices which were initially at a pitch of about 38 mm, were heated to approximately 120°C prior to contacting the sheet.

The composite plastics film thus produced and having an average thickness of 0.094 mm and nominal substance of 75 gsm was cooled, edge trimmed and passed through a corona discharge treatment unit adjusted to give a treatment level such that the wettability of the surface of each outer layer was greater than 40 dynes/cm and then reeled.

The wettability of the product was determined by the application of Sherman Surface Tension Ink 45 dynes cm⁻¹, formulated to demonstrate a wettability of at least 45 dynes/cm.

The production equipment remained clear of undesirable deposits and the product was dust free.

The physical properties of the product were as follows:

		<u>LHS</u>		<u>RHS</u>	
		<u>MD</u>	<u>TD</u>	<u>MD</u>	<u>TD</u>
5	Tensile strength (Nmm ⁻²)	43.75	38.02	41.02	37.76
10	% elongation at break	238	277	241	293
15	Trouser tear Strength (Nmm ⁻¹)	134.81	161.26	110.52	135.8
20	Surface cohesive strength, N				
	Face A, Face B	7.7		7.9	
25	Stiffness BSTM 2782 (Kg m ⁻¹)	2.58	3.11	2.50	3.0
30	Static Decay After 1 day ($\frac{1}{2}$ life seconds)	4.5	6.3	10.3	17.4
35	Face A, Face B				
	Gloss 85°	23.24	14.14	20.21	13.11
40	Face A, Face B				

The thickness distribution of the layers in the final product was on average:

Outer 0.005 mm

Core 0.084 mm

45 Outer 0.005 mm

The product had a paper-like feel and the outer layers exhibited external printable surfaces having a paper-like appearance and excellent write-on qualities with both ballpoint pen and pencil. Further, the erasability of pencilled writing using a conventional rubber eraser was also excellent.

50 Example 2

The procedure of Example 1 was repeated to produce a stretched product having the same nominal substance level of 75 gsm but with the average thickness distribution of the layers being:

Outer 0.006 mm

55 Core 0.082 mm

Outer 0.006 mm

This was achieved by increasing the speed of the secondary extruder by about 17%.

The physical properties of the product were very similar to those of Example 1 but with a notable improve-

ment in Static Decay values which were:-

	<u>LHS</u>		<u>RHS</u>	
	<u>MD</u>	<u>TD</u>	<u>MD</u>	<u>TD</u>
5	After 1 day			
	$\frac{1}{2}$ life			
	(seconds)			
10	3.9	5.7	1.53	2.06

A comparison of the static decay profiles obtained from measurements across the webs for the products of Example 1 and Example 2 after 10 days ageing revealed a maximum decay time of 12 seconds for Example 2 material as opposed to a maximum, albeit more localised, of 65 seconds for Example 1 material.

The feel and surface qualities of the product of Example 2 were comparable with those of Example 1.

Example 3

The procedure of Example 1 was repeated with the conditions adjusted to give an initial conditioned composite sheet extrudate of overall thickness 1.5 mm with the core material thickness being 1.32 mm and outer layers each having a thickness of 0.09 mm. The rate of extrusion was 360 Kg/hr. In addition the composition used for each of the outer layers was modified to comprise the following:-

	<u>Parts by weight</u>
25	Rigidex 002/55 100
	Innovex (as in compound B of Ex 1) 25
	Titanium dioxide (Rutile)
30	RCR2 19.5
	Calcium Carbonate (as in Compound B of Ex 1) 7.5
	Rigidex DFDG 0159 7.5
35	Calcium Stearate (as in Compound B of Ex 1) 0.075
	Rigidex HD 6070EA 3
	Armostat 400 (antistatic active ingredient 75%) 0.03
	Nourymix AS024 (antistatic active ingredient 40%) 0.4
40	Polystyrene HF888 25
	Cariflex TR1102 4

The A and B masterbatches and compounding procedure was otherwise as described in Example 1 and the remaining extrusion, stretching and treatment conditions were essentially as described in Example 1.

The composite plastics film thus produced had an average thickness of 0.088 mm and a nominal substance of 70 gsm.

The physical properties of the product were as follows:-

50

55

		<u>LHS</u>		<u>RHS</u>	
		<u>MD</u>	<u>TD</u>	<u>MD</u>	<u>TD</u>
5	Tensile strength (Nmm ⁻²)	45.57	39.8	46.14	32.63
10	% Elongation at break	146	229	152	187
15	Trouser tear Strength (Nmm ⁻¹)	127.33	162.91	131.92	159.62
20	Surface Cohesive strength, N Face A, Face B	7.63	7.59	10.08	8.32
25					
		<u>LHS</u>		<u>RHS</u>	
		<u>MD</u>	<u>TD</u>	<u>MD</u>	<u>TD</u>
30	Stiffness (BSTM 2782) (Kg m ⁻¹)	1.63	2.0	1.96	2.07
35	Static Decay ½ life (seconds) after 1 day	> 1 min		> 1 min	
40	Gloss 85° Face A, Face B	37.8	25.5	33.4	19.7

The thickness distribution of the layers in the product was on average approximately:-

Outer 0.005 mm
Core 0.078 mm
45 Outer 0.005 mm

While the product had a paper-like feel and the outer surfaces exhibited good printable surface qualities having paper-like appearance and excellent write-on and erasability qualities as described for the product of Example 1; the product was subsequently coated on both sides with a coating of the type described in our GB-A-2177413 in order to achieve a dried coated product with a nominal substance of 90 gsm.

50 The physical properties of the coated product were as follows:-

	<u>MD</u>	<u>TD</u>
5		
Tensile strength (Nmm ⁻²)	38.6	28.6
% Elongation at break	135	143
10		
Trouser tear Strength (Nmm ⁻¹)	130.07	102.08
15		
	<u>MD</u>	<u>TD</u>
Surface Cohesive strength, N		
Face A, Face B	7.66	8.06
20		
(no coating pick)		
Stiffness (BSTM 2782) (Kg m ⁻¹)	4.65	4.72
25		
Static Decay ½ life after 1 day (seconds)		0.5
30		
Gloss 85° Face A, Face B	14.5	14.5
35		

The coated product exhibited enhanced paper-like qualities including stiffness, printability and antistatic qualities making it an excellent synthetic paper product.

40 Microscope examination of the surfaces of the outer layers of the uncoated composite products of Examples 1 to 3 showed the surfaces to contain substantially no open voids. Examination of a cross-section of each of the products showed them each to have a core of voided (multicellular) structure having on each side a void free outer layer.

45 Example 4

The procedure of Example 1 was repeated with the following modifications:-
The following composition was used to produce Compound B:-

	<u>Parts by weight</u>
50	
Rigidex 002/55	100
Appryl propylene polymer (supplied by Appryl SNC)	13.73
55	
Rigidex HD6070EA	6.21
Rigidex DFDG 0159	2.93
EPDM rubber	2.80

	<u>Parts by weight</u>
Titanium dioxide RCR2	15.28
Calcium Carbonate	25.36
5 Calcium Stearate	0.09
Dispersing Agent	0.25
(for CaCO ₃ in EPDM rubber)	
10 Nourymix AS024 (40% active ingredient)	3.3

The masterbatches B1 and B2 were replaced by the following:-

B4 and B5 equivalent respectively to A1 and A2 of Example 1 plus B6 comprising Omyalene G200 (supplied by OMYA SNC a subsidiary of Croxton and Garry Ltd) containing:-

15 Calcium Carbonate	88%
EPDM rubber binder	11%
Dispersing Agent	1%

Masterbatches B4, B5 and B6 were intermixed in appropriate proportions with the remainder of the ingredients of the above composition and fed to a compounding extruder. The composition was melt blended at approximately 200°C extruded, cooled and diced to form Example 4 Compound B.

The procedure of Example 1 was then continued with Compound A and Example 4 Compound B being fed to the in-line and secondary extruders respectively. The remaining extrusion, stretching and treatment conditions were carried out essentially as described in Example 1 with the exception that the temperatures in the four zone circulating air oven were as follows:-

25 Preheat 1	136°C
Preheat 2	129°C
Stretching 3	120°C
Annealing 4	112°C

A product having similar properties was obtained.

30 It was noted that during the extrusion of the composite extrudate in this Example no die deposit was observed as was also the case in Examples 1, 2 and 3. This was attributed to the use of the mixture of the thermoplastics resins and the rubbery polymer in the outer layers in accordance with this invention.

Comparative Example 5

35 The procedure of Example 1 was repeated with modifications as follows:-
The following composition was used to produce Compound B:-

	<u>Parts by weight</u>
40 Rigidex 002/55	100
Appryl propylene polymer	15.6
Rigidex HD6070EA	23.8
45 Rigidex DFDG 0159	3.3
Titanium Dioxide RCR2	17.3
Calcium Carbonate	28.7
50 Calcium Stearate	0.1
Armostat 400	0.17
Nourymix AS024 (40% active ingredient)	3.8

55 The masterbatches B1 and B2 were replaced by B7, B8, and B9 equivalent respectively to B1, B2 and A2 of Example 1.

The masterbatches B7, B8 and B9 were intermixed in appropriate proportions with the remainder of the ingredients of the above composition and fed to a compounding extruder. The composition was melt blended

at approximately 200°C, extruded, cooled and diced to form Comparative Example 5 Compound B.

The procedure of Example 1 was then continued with Compound A and Comparative Example 5 Compound B being fed to the in-line and secondary extruders respectively. The remaining extrusion, stretching and treatment conditions were carried out substantially as in Example 4.

5 While no die deposit was observed during the coextrusion, surface splitting and delamination of the outer layer from the core layer of the stretched product under test revealed bad surface cohesion and bad outer layer to core adhesion which was in clear contrast to the stretched products of Examples 1 to 4.

The test for surface cohesive strength and outer layer adhesion as applied to all the stretched uncoated products of Examples 1 to 5 was as follows:-

10 A 10 cm long strip of approximately 1" wide Sellotape adhesive tape was applied to the surface with light finger pressure. This was then immediately removed using a Lloyd Instruments Ltd tensometer, the crossheads diverging at a speed of 500 mm/min. The resulting test pieces were examined for 1) destruction of the surface layer by the adhesive tape and 2) delamination of the surface layer from the core layer. Where either of the above were apparent a 'bad' result was recorded, otherwise the sample was classed as 'good'.

15 The results may be summarised as follows:-

20	EXAMPLE	1	2	3	4	5
25						
30	SURFACE COHESION	*	*	*	*	+
35						
40	OUTER LAYER ADHESION TO CORE LAYER	*	*	*	*	+
45						

* = good + = bad

50 It will be appreciated from the above results that the rubbery polymer omitted from the Comparative Example 5 is an important component of the outer layer destined to provide an external printable surface, in order to achieve acceptable cohesive and adhesive bond strengths in composite products derived from a simple coextrusion, with avoidance of die crust problems, and a stretching operation to stretch-void a core layer.

55 It will also be appreciated that the products of this invention, whether or not provided with a coating, may find applications in the stationery, printing, book-binding and label industries. In the latter sense particularly, use for labels employed in the in-mould labelling of containers produced by for example, blow-moulding and/or injection moulding or thermoforming processes can have considerable advantages in providing durability and feasibility of reworking or recycling label-bearing plastics containers. In such applications the use of adhesives

of known types, contact or heat activatable adhesives for example, may assist bonding where necessary, particularly when the relevant outer layer to be bonded carries a chalk or clay-type coating for example.

5 Claims

1. A composite film or sheet for use as synthetic paper comprising three coextruded layers including a core layer situated between two outer layers, the core layer having been stretch-voided, characterised in that at least one of the outer layers provides an external printable surface, optionally after further treatment, and comprises at least three thermoplastics polymeric materials of which one is a rubbery polymer and at least a further two of the materials have at least a degree of mutual incompatibility, said external surface being substantially free of particle-induced open voids.
2. A composite as claimed in Claim 1 wherein the thermoplastics material on which the compositions of the outer layers are principally based are at least similar to that which predominates in the core layer.
3. A composite as claimed in Claim 1 or 2 wherein the core layer is derived from a composition selected from those described in GB-A-1470372 and GB-A-1492771.
4. A composite as claimed in Claim 3 wherein the core layer is derived from a composition comprising a blend of an orientable thermoplastics olefin polymer and from 2 to 50% by weight calculated on the blend of at least one metal resinate which at least in part comprises a separate phase uniformly distributed within the olefin polymer and which composition is extrudable to form a layer and stretchable to produce a voided structure.
5. A composite as claimed in Claim 4 wherein the core layer is derived from a composition comprising a blend of high density polyethylene (as herein before defined) and a calcium-zinc resinate.
6. A composite as claimed in any one of the preceding Claims wherein voids in the core layer are solely due to stretch-voiding.
7. A composite according to any one of the preceding Claims wherein the outer layers are bonded directly to the core layer.
8. A composite according to any one of the preceding Claims wherein at least one layer providing an external printable surface is based on a thermoplastics material that is not water-vapour absorbent and is free of particulate or microfibrinous hygroscopic solid polymeric additive capable of rendering the layer water-vapour absorbent.
9. A composite according to any one of the preceding Claims wherein at least the outer layer providing an external printable surface is translucent or opaque.
10. A composite according to Claim 5 wherein at least the outer layer providing the external printable surface is based on high density polyethylene as herein before defined.
11. A composite according to any one of the preceding Claims wherein at least one of the outer layers is based on a thermoplastics composition comprising at least high density polyethylene, polystyrene and a rubbery polymer with or without linear low density polyethylene.
12. A composite according to any one of Claims 1 to 10 wherein at least one of the outer layers is based on a thermoplastics composition comprising high density polyethylene and linear low density polyethylene or a propylene (co)polymer and a rubbery polymer.
13. A composite according to any one of Claims 10, 11 or 12 wherein the high density polyethylene has a Melt Flow Index in the range 0.001 to 2.0, preferably 0.15 to 0.5 decigrams/minute.
14. A composite according to any one of the preceding Claims wherein the rubbery polymer is selected from thermoplastics copolymers of butadiene and styrene, copolymers of isobutylene and isoprene, and ter-

polymers of ethylene, propylene and a diene.

- 5 15. A composite according to any one of the preceding Claims wherein the amount of rubbery polymer present in the outer layer destined to provide an external printable surface is in the range of 0.5 to 20, preferably 1 to 10 parts by weight, based on 100 parts by weight of the principal thermoplastics polymer component of the outer layer.
- 10 16. A composite according to any one of the preceding Claims wherein the outer layers contain an amount of antistatic agent effective in reducing static decay half-life of the composite after ageing for one day to no more than 60 secs.
- 15 17. A composite according to Claim 16 wherein the antistatic agent is present in the outer layers at from 0.5 to 1.5 parts by weight per 100 parts of the principal polymer component of the composition comprising each outer layer.
18. A composite according to any one of the preceding Claims wherein the outer layers have a pigment/filler content in the range 10 - 30%, preferably 15 - 25% by weight, based on the weight of the composition of each outer layer.
- 20 19. A composite according to any one of the preceding Claims wherein the core layer is stretch-voided at a temperature within the normal orientation temperature range of the principal thermoplastics polymer on which the core layer is based.
- 25 20. A composite according to Claim 19 wherein the temperature of stretching is selected from:
 - a) temperatures below the melting point or softening point of the void inducing component of the core layer when said component is a non-polymeric organic compound, a metal salt of an organic acid, a metal resinate or a modified or unmodified rosin ester;
 - b) temperatures below the glass transition temperature of the void inducing component of the core layer when said component is a polymer;
 such that voids are formed in the core layer.
- 30 21. A composite according to any one of the preceding Claims wherein the core layer is stretch-voided at a temperature within the normal orientation temperature range of the principal thermoplastics polymer on which the outer layer providing an external printable surface is based.
- 35 22. A composite according to any one of the preceding Claims wherein the core layer is stretch-voided by biaxial stretching.
- 40 23. A composite according to Claim 22 wherein the biaxial stretching is simultaneous biaxial stretching.
24. A composite according to any one of the preceding Claims wherein the core layer is stretch-voided by use of a flat-bed stretcher.
- 45 25. A composite according to any one of the preceding Claims wherein the core layer incorporates reworked, reclaimed scrap composite material.
26. A composite according to any one of the preceding Claims wherein the thickness of at least one layer providing an external printable surface is no more than 25% of the thickness of the core layer.
- 50 27. A composite according to any one of the preceding Claims which is corona discharge treated.
28. A composite according to any one of the preceding Claims which is further coated on at least one side.
29. A composite according to Claim 28 wherein the coating is selected from those described in GB-A-2177413.
- 55 30. A composite according to any one of the preceding Claims which comprises a synthetic paper.
31. A method for producing a composite plastics film or sheet as claimed in any one of the preceding Claims

which comprises coextruding three thermoplastics layers comprising a core layer situated between two outer layers wherein the composition of the core-layer is stretch-voidable and wherein the composition of at least one of the outer layers is stretchable at a temperature at which the core layer is stretch-voidable, stretch-voiding the core layer and stretching the outer layers to produce an external printable surface, optionally after further treatment, and optionally coating the stretched product.

- 5
32. A method as claimed in Claim 31 wherein the stretch-voiding of the core layer and stretching of the outer layers occur simultaneously.
- 10
33. A method as claimed in Claims 31 or 32 wherein the temperature of stretching is within the normal orientation temperature range of the principal thermoplastics polymer on which the core layer is based.
- 15
34. A method as claimed in Claim 33 wherein the temperature of stretching is selected from:
a) temperatures below the melting point or softening point of the void inducing component of the core layer when said component is a non-polymeric organic compound, a metal salt of an organic acid, a metal resinate or a modified or unmodified rosin ester;
b) temperatures below the glass transition temperature of the void inducing component of the core layer when said component is a polymer;
such that voids are formed in the core layer.
- 20
35. A method as claimed in any one of Claims 31 to 34 wherein the core layer is stretch-voided at a temperature within the normal orientation temperature range of the principal thermoplastics polymer on which the outer layer destined to provide an external printable surface is based.
- 25
36. A method as claimed in any one of the Claims 31 to 35 wherein the stretch-voiding of the core layer and the stretching of the outer layers are achieved by stretching the coextrudate simultaneously biaxially in the machine and in transverse directions.
- 30
37. A method as claimed in any one of Claims 31 to 36 wherein reworked, reclaimed scrap composite material is incorporated into the composition of the core layer.
38. A composite according to any one of Claims 1 to 30 used as an article of stationery or in printing, book binding or labelling.
- 35
39. A composite according to Claim 38 when used in the in-mould labelling of a plastics container.

40

45

50

55



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number : **0 470 760 A3**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number : 91307049.6

(51) Int. Cl.⁵ : **B32B 27/08**

(22) Date of filing : 31.07.91

(30) Priority : 09.08.90 GB 9017500
17.08.90 GB 9018056

(43) Date of publication of application :
12.02.92 Bulletin 92/07

(84) Designated Contracting States :
DE FR GB IT

(88) Date of deferred publication of search report :
01.07.92 Bulletin 92/27

(71) Applicant : **BXL Plastics Limited**
Belgrave House, 76 Buckingham Palace Road
London SW1W 0SU (GB)

(72) Inventor : **Leese, Leonard**
6 Valley Close, Brantham
Manningtree, Essex CO11 1GG (GB)
Inventor : **Yadav, Vijay**
14309 Blue Granite Road
Pineville, North Carolina 28134 (US)

(74) Representative : **Krishnan, Suryanarayana**
Kalyana et al
BP INTERNATIONAL LIMITED Patents &
Agreements Division Chertsey Road
Sunbury-on-Thames Middlesex TW16 7LN
(GB)

(54) **Composite plastics film or sheet.**

(57) This invention relates to a composite film comprising three coextruded layers including a core layer sandwiched between two outer layers, the core layer having been stretch-voided. At least one of the outer layers has an external printable surface and comprises at least three thermoplastic polymeric materials of which one is a rubbery polymer and at least a further two of the materials have a degree of mutual incompatibility, said external printable surface being substantially free of particle-induced voids. The films are suitable for use as synthetic paper.

EP 0 470 760 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number

EP 91 30 7049

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
A X	EP-A-0 216 343 (HOECHST AKTIENGESELLSCHAFT) * examples 1,2 * ---	1,2 31-36	B32B27/08
A	EP-A-0 137 454 (ASAHI KASEI KOGYO KABUSHIKI KAISHA) * claims 1,16 * ---	1,2	
A	EP-A-0 321 843 (HOECHST AKTIENGESELLSCHAFT) * claims *	1,2	
A	EP-A-0 127 252 (MOBIL OIL CORPORATION) * claims * -----	1,2	
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			B32B
Place of search THE HAGUE		Date of completion of the search 24 APRIL 1992	Examiner DE JONGE S. J. P.
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1501 01.92 (P0401)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER:** _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)